



Sealing for a safer and greener tomorrow

# Chemical Compatibility Chart

## Compressed Fiber Gasket Materials

A: Suitable    B: Consult with TEADIT    C: Not recommended

FLUIDS	NA1001	NA1082SAN	NA1076	NA1080	NA1081	NA1085	NA1100	NA1122
Acetaldehyde	B	B	C	B	B	C	B	B
Acetamida	A	A	B	C	A	B	A	A
Acetic Acid (T< 190F)	A	A	A	A	A	A	A	A
Acetic Acid (T≥ 190F)	C	C	-	C	C	A	C	C
Acetic Anhydride	C	C	B	C	C	A	C	C
Acetone	C	C	C	B	C	B	C	C
Acetonitrile	C	C	-	-	C	-	C	C
Acetophenone	C	C	C	C	C	C	C	C
Acetylene	A	A	B	A	A	B	A	C
Acrylic Acid	B	B	-	-	B	-	B	B
Acrylonitrile	C	C	C	C	C	C	C	C
Adipic Acid	A	A	A	B	A	A	A	A
Air	A	A	A	A	A	A	A	A
Aluminum Acetate	A	A	B	A	A	A	A	A
Aluminum Chloride	A	A	A	A	A	A	A	A
Aluminum Fluoride	A	A	A	A	A	A	A	A
Aluminum Nitrate	A	A	A	A	A	A	A	A
Aluminum Sulfate	A	A	A	B	A	A	A	A
Alums	A	A	-	A	A	A	A	A
Ammonia – Cold (Gas)	A	A	A	A	A	A	A	C
Ammonia – Hot (Gas)	C	C	B	C	C	B	C	C
Ammonia – Liquid, Anhydrous	B	B	A	C	B	B	B	B
Ammonium Carbonate	C	C	A	A	C	C	C	C
Ammonium Chloride	A	A	A	A	A	A	A	A
Ammonium Hydroxide 30% (T<120F)	A	A	A	C	A	A	A	A
Ammonium Nitrate	A	A	A	A	A	A	A	A
Ammonium Phosphate	A	A	A	A	A	A	A	A
Ammonium Sulfate	A	A	A	B	A	A	A	A
Amyl Acetate	B	B	C	B	B	C	B	B
Amyl Alcohol	B	B	B	A	B	A	B	B
Aniline	C	C	C	B	C	C	C	C
Aniline Dyes	C	C	B	B	C	B	C	C
Anon (Cyclohexanone)	C	C	C	C	C	C	C	C
Aqua Regia	C	C	C	C	C	C	C	C
Aroclors	C	C	B	C	C	C	C	C
Asphalt	B	B	B	C	B	B	B	B
Barium Chloride	A	A	A	A	A	A	A	A
Barium Hydroxide	A	A	A	A	A	A	A	A
Barium Sulfide	A	A	A	B	A	A	A	A
Beer	A	A	A	A	A	A	A	A
Benzaldehyde	C	C	C	C	C	-	C	C

\*Please see note at the end of this table.

R.072816

**Teadit North America.**

10545 Red Bluff Rd - Pasadena - TX - 77507

Phone: 281-476-3900 - Fax: 281-476-3999 - e-mail: sales@teadit.com - engineering@teadit.com - [www.teadit-na.com](http://www.teadit-na.com)



Sealing for a safer and greener tomorrow

# Chemical Compatibility Chart

## Compressed Fiber Gasket Materials

A: Suitable    B: Consult with TEADIT    C: Not recommended

FLUIDS	NA1001	NA1082SAN	NA1076	NA1080	NA1081	NA1085	NA1100	NA1122
Benzene	C	C	C	C	C	C	C	C
Benzoic Acid	B	B	C	B	B	B	B	B
Benzoyl Chloride	C	C	C	C	C	C	C	C
Benzyl Alcohol	C	C	B	C	C	B	C	C
Benzyl Chloride	C	C	C	C	C	C	C	C
Biphenyl	C	C	C	C	C	C	C	C
Blast Furnace Gas	C	C	C	C	C	C	C	C
Bleach (Sodium Hypochlorite)	C	C	C	C	C	B	C	C
Boiler Feeder Water	A	A	A	A	A	A	A	A
Borax	B	B	A	B	B	A	B	B
Boric Acid	A	A	A	A	A	A	A	A
Brines	A	A	A	A	A	A	A	A
Bromine	C	C	C	C	C	C	C	C
Bromine Trifluoride	C	C	C	C	C	C	C	C
Butadiene	C	C	C	C	C	B	C	C
Butane	A	A	A	C	A	A	A	C
Butanone (MEK)	C	C	C	C	C	C	C	C
Butyl Acetate	B	B	C	C	B	C	B	B
Butyl Alcohol (Butanol)	A	A	A	A	A	A	A	A
n-Butyl Amine	B	C	C	C	C	C	C	C
Butyl Methacrylate	C	C	-	C	C	C	C	C
Butyric Acid	C	C	-	C	C	C	C	C
Calcium Bisulfite	C	C	A	C	C	A	C	C
Calcium Chloride	A	A	A	A	A	A	A	A
Calcium Hydroxide (T<120F)	A	A	A	A	A	A	A	A
Calcium Hypochlorite	B	B	C	C	B	A	B	B
Calcium Nitrate	A	A	A	A	A	A	A	A
Cane Sugar Liquors	A	A	A	A	A	A	A	A
Carbolic Acid, Phenol	C	C	C	C	C	C	C	C
Carbon Dioxide, Dry	A	A	B	A	A	A	A	B
Carbon Dioxide, Wet	A	A	B	A	A	A	A	B
Carbon Disulfide	C	C	C	C	C	C	C	C
Carbon Monoxide	A	A	B	B	A	B	A	B
Carbon Tetrachloride	B	B	C	C	B	C	B	B
Carbonic Acid	B	B	A	B	B	B	B	B
Castor Oil	A	A	A	A	A	A	A	A
Cetane (Hexadecane)	A	A	-	C	A	B	A	B
China Wood Oil	A	A	B	C	A	C	A	A
Chlordane	B	B	-	C	B	C	B	B
Chlorinated Solvents	C	C	C	C	C	C	C	C
Chlorine (Dry)	B	B	C	B	B	B	B	C

\*Please see note at the end of this table.



Sealing for a safer and greener tomorrow

# Chemical Compatibility Chart

## Compressed Fiber Gasket Materials

A: Suitable    B: Consult with TEADIT    C: Not recommended

FLUIDS	NA1001	NA1082SAN	NA1076	NA1080	NA1081	NA1085	NA1100	NA1122
Chlorine (Wet)	C	C	C	C	C	C	C	C
Chlorine Dioxide	C	C	C	C	C	C	C	C
Chlorine Trifluoride	C	C	C	C	C	C	C	C
Chloroacetic Acid	C	C	C	C	C	A	C	C
Chlorobenzene	C	C	C	C	C	C	C	C
Chloroform	C	C	C	C	C	C	C	C
Chloroprene	C	C	-	-	C	-	C	C
Chlorosulfonic Acid	C	C	C	C	C	C	C	C
Chrome Plating Solutions	C	C	C	C	C	C	C	C
Chromic Acid	C	C	C	C	C	C	C	C
Citric Acid	A	A	A	A	A	A	A	A
Coke Oven Gas	C	C	C	C	C	C	C	C
Condensate	A	A	A	A	A	A	A	A
Copper Acetate	B	B	B	C	B	C	B	B
Copper Chloride	A	A	B	A	A	A	A	A
Copper Sulfate (T<120F)	A	A	A	A	A	A	A	A
Corn Oil	A	A	C	C	A	B	A	A
Cotton Seed Oil	A	A	B	C	A	B	A	A
Creosote	A	A	B	C	A	C	A	A
Cresol	B	B	C	C	B	C	B	B
Crude Oil	B	B	-	C	B	C	B	B
Cumene	C	C	C	C	C	C	C	C
Cyclohexane	A	A	C	C	A	C	A	A
Cyclohexanone	C	C	C	C	C	C	C	C
Cyclohexyl Alcohol	A	A	-	C	A	B	A	A
Decane	A	A	C	C	A	C	A	A
Detergent Solutions	A	A	B	B	A	B	A	A
Dibenzyl Ether	C	C	C	C	C	C	C	C
Dibromethane	C	C	-	C	C	C	C	C
Dibutyl Phthalate	C	C	C	C	C	C	C	C
Dibutyl Sebacate	C	C	C	C	C	C	C	C
o-Dichlorobenzene	C	C	C	C	C	C	C	C
Dichloroethane (1,1 or 1,2)	C	C	-	C	C	-	C	C
Diesel Oil	A	A	C	C	A	B	A	A
Diethanolamine	A	A	-	-	A	-	A	A
Diethyl Ether	C	C	C	C	C	C	C	C
N,N-Dimethyl Aniline	C	C	C	C	C	C	C	C
Dimethyl Ether	A	A	C	C	A	C	A	B
Dimethyl Formamide	C	C	C	C	C	C	C	C
Dimethyl Phthalate	C	C	C	C	C	C	C	C
2,4-Dinitrotoluene	C	C	C	C	C	C	C	C

\*Please see note at the end of this table.

R.072816

**Teadit North America.**

10545 Red Bluff Rd - Pasadena - TX - 77507

Phone: 281-476-3900 - Fax: 281-476-3999 - e-mail: sales@teadit.com - engineering@teadit.com - [www.teadit-na.com](http://www.teadit-na.com)



Sealing for a safer and greener tomorrow

# Chemical Compatibility Chart

## Compressed Fiber Gasket Materials

A: Suitable    B: Consult with TEADIT    C: Not recommended

FLUIDS	NA1001	NA1082SAN	NA1076	NA1080	NA1081	NA1085	NA1100	NA1122
Dioxane	C	C	C	C	C	C	C	C
Dowtherm 4000	-	B	-	B	B	-	B	-
Dowtherm	C	C	C	C	C	C	C	C
Epichlorohydrin	C	C	C	C	C	B	C	C
Ethane	B	B	B	B	B	B	B	C
Ethers	C	C	C	C	C	C	C	C
Ethyl Acetate	C	C	C	C	C	C	C	C
Ethyl Acrylate	C	C	C	C	C	C	C	C
Ethyl Alcohol (Ethanol)	A	A	A	A	A	A	A	A
Ethyl Benzene	C	C	C	C	C	C	C	C
Ethyl Cellulose	B	B	B	B	B	B	B	B
Ethyl Chloride	B	B	C	C	B	C	B	B
Ethyl Ether	B	B	C	C	B	B	B	B
Ethylene	A	A	C	B	A	C	A	C
Ethylene Dibromide	C	C	-	C	C	C	C	C
Ethylene Dichloride	C	C	C	C	C	C	C	C
Ethylene Glycol	A	A	A	A	A	A	A	A
Ethylene Oxide	C	C	C	C	C	C	C	C
Ferric Chloride	A	A	A	A	A	B	A	A
Ferric Sulfate	A	A	A	A	A	A	A	A
Fluorine, Gas	C	C	-	C	C	-	C	C
Fluorine, Liquid	C	C	C	C	C	-	C	C
Fluorosilicic Acid	A	A	B	C	A	A	A	A
Formaldehyde	A	A	B	B	A	B	A	A
Formic Acid 10%	B	B	A	A	B	A	B	B
Formic Acid 85%	B	B	A	A	B	A	B	B
Freon 12	A	A	A	A	A	A	A	C
Freon 22	C	C	A	A	C	A	C	C
Freon 32	A	A	A	A	A	A	A	C
Fuel Oil	A	A	B	C	A	C	A	A
Furfural	C	C	C	C	C	C	C	C
Gasoline, Refined	A	A	C	C	A	C	A	A
Gasoline, Sour	A	A	C	C	A	C	A	A
Gelatin	A	A	A	A	A	A	A	A
Glucose	A	A	A	A	A	A	A	A
Glue, Protein Base	A	A	A	A	A	A	A	A
Glycerine, Glycerol	A	A	A	A	A	A	A	A
Glycol	A	A	A	A	A	A	A	A
Grease	A	A	-	C	A	C	A	A
Green Sulfate Liquor	B	B	B	B	B	B	B	B
Heptane	A	A	-	C	A	B	A	A

\*Please see note at the end of this table.

R.072816

**Teadit North America.**

10545 Red Bluff Rd - Pasadena - TX - 77507

Phone: 281-476-3900 - Fax: 281-476-3999 - e-mail: sales@teadit.com - engineering@teadit.com - [www.teadit-na.com](http://www.teadit-na.com)



Sealing for a safer and greener tomorrow

# Chemical Compatibility Chart

## Compressed Fiber Gasket Materials

A: Suitable    B: Consult with TEADIT    C: Not recommended

FLUIDS	NA1001	NA1082SAN	NA1076	NA1080	NA1081	NA1085	NA1100	NA1122
Hexane	A	A	B	C	A	A	A	A
Hexone	B	B	-	-	B	-	B	B
Hydraulic Oil (Mineral)	A	A	B	C	A	B	A	A
Hydrazine	B	B	B	B	B	B	B	B
Hydrobromic Acid	C	C	C	C	C	A	C	C
Hydrochloric Acid 10%	A	A	C	C	A	A	A	A
Hydrochloric Acid 37%	C	C	C	C	C	A	C	C
Hydrofluoric Acid	C	C	C	C	C	C	C	C
Hydrofluosilicic Acid	C	C	B	C	C	A	C	C
Hydrogen	A	A	A	A	A	A	A	B
Hydrogen Fluoride	C	C	-	C	C	-	C	C
Hydrogen Peroxide < 30%	A	A	C	B	A	B	A	A
Hydrogen Sulfide, Dry or Wet	C	C	C	C	C	B	C	C
Hydroquinone	B	B	C	C	B	C	B	B
Iodine Pentafluoride	C	C	C	C	C	C	C	C
Isooctane	A	A	B	C	A	A	A	A
Isophorone	C	C	C	C	C	C	C	C
Isopropyl Alcohol	A	A	B	A	A	A	A	A
Kerosene	A	A	B	C	A	C	A	A
Lacquers	C	C	C	C	C	C	C	C
Lactic Acid 50%	A	A	-	A	A	A	A	A
Lactic Acid, Cold	A	A	A	A	A	A	A	A
Hot	C	C	C	C	C	C	C	C
Lead Acetate (Sugar of Lead)	B	B	B	C	B	C	B	B
Linseed Oil	A	A	B	C	A	B	A	A
Liquified Petroleum Gas (LPG)	A	A	B	C	A	B	A	C
Lubricating Oils, Mineral or Petroleum Types	A	A	B	C	A	C	A	A
Lye	B	B	B	B	B	A	B	B
Magnesium Chloride	A	A	A	A	A	A	A	A
Magnesium Hydroxide (T<120F)	B	B	A	B	B	A	B	B
Magnesium Sulfate	A	A	A	A	A	A	A	A
Maleic Acid	C	C	C	C	C	C	C	C
Maleic Anhydride	C	C	C	C	C	C	C	C
Mercuric Chloride	A	A	A	A	A	A	A	A
Mercury	A	A	A	A	A	A	A	A
Methane	A	A	B	C	A	B	A	C
Methyl Alcohol (Methanol)	A	A	A	A	A	A	A	A
Methylacrylic Acid	C	C	B	C	C	C	C	C
Methyl Bromide	C	C	C	C	C	C	C	C
Methyl Chloride	C	C	C	C	C	C	C	C
Methyl Chloroform	C	C	-	-	C	-	C	C

\*Please see note at the end of this table.

R.072816

**Teadit North America.**

10545 Red Bluff Rd - Pasadena - TX - 77507

Phone: 281-476-3900 - Fax: 281-476-3999 - e-mail: sales@teadit.com - engineering@teadit.com - [www.teadit-na.com](http://www.teadit-na.com)



Sealing for a safer and greener tomorrow

# Chemical Compatibility Chart

## Compressed Fiber Gasket Materials

A: Suitable    B: Consult with TEADIT    C: Not recommended

FLUIDS	NA1001	NA1082SAN	NA1076	NA1080	NA1081	NA1085	NA1100	NA1122
Methyl Ethyl Ketone	C	C	C	C	C	C	C	C
Methyl Iodide	C	C	-	-	C	-	C	C
Methyl Isobutyl Ketone (MIBK)	C	C	C	C	C	C	C	C
Methyl Methacrylate	C	C	C	C	C	C	C	C
Methyl tert-Butyl Ether (MTBE)	A	A	-	-	A	-	A	A
Milk	A	A	A	A	A	A	A	A
Mineral Oil	A	A	B	C	A	B	A	A
Naphtha	A	A	C	C	A	C	A	A
Naphthalene	C	C	C	C	C	C	C	C
Natural Gas - GLP	A	A	A	B	A	A	A	C
Nickel Chloride	A	A	A	A	A	A	A	A
Nickel Sulfate	A	A	A	B	A	A	A	A
Nitric Acid ≤50% (T<120F)	C	C	B	C	C	A	C	C
Nitric Acid >50%	C	C	C	C	C	C	C	C
Nitric Acid Crude	C	C	C	C	C	C	C	C
Nitrobenzene	C	C	C	C	C	C	C	C
Nitrogen	A	A	A	A	A	A	A	A
Nitrogen Tetroxide	C	C	C	C	C	C	C	C
Nitromethane	C	C	B	C	C	C	C	C
2-Nitropropane	C	C	-	C	C	C	C	C
Octane	A	A	B	C	A	C	A	A
Oleic Acid	A	A	C	C	A	B	A	A
Orthodichlorobenzene	C	C	C	C	C	C	C	C
Oxalic Acid	B	B	B	B	B	B	B	B
Oxygen	C	C	C	C	C	B	C	C
Ozone	C	C	C	C	C	A	C	C
Palmitic Acid	A	A	B	B	A	B	A	A
Pentachlorophenol	A	A	-	-	A	-	A	A
Pentane	A	A	-	C	A	B	A	A
Perchloric Acid	C	C	B	C	C	C	C	C
Perchloroethylene	B	B	C	C	B	C	B	B
Petroleum	A	A	B	B	A	B	A	A
Petroleum Oils	A	A	B	C	A	B	A	A
Petroleum Ether	A	A	B	C	A	A	A	A
Phenol	C	C	C	C	C	C	C	C
Phosphoric Acid	C	C	B	C	C	C	C	C
Picric Acid	B	B	A	B	B	B	B	B
Pinene	B	B	C	C	B	C	B	B
Piperidine	C	C	C	C	C	C	C	C
Polychlorinated Biphenyls	B	B	-	-	B	-	B	-
Potassium Acetate	A	A	B	B	A	C	A	A

\*Please see note at the end of this table.

R.072816

**Teadit North America.**

10545 Red Bluff Rd - Pasadena - TX - 77507

Phone: 281-476-3900 - Fax: 281-476-3999 - e-mail: sales@teadit.com - engineering@teadit.com - [www.teadit-na.com](http://www.teadit-na.com)



Sealing for a safer and greener tomorrow

# Chemical Compatibility Chart

## Compressed Fiber Gasket Materials

A: Suitable    B: Consult with TEADIT    C: Not recommended

FLUIDS	NA1001	NA1082SAN	NA1076	NA1080	NA1081	NA1085	NA1100	NA1122
Potassium Chloride	A	A	A	A	A	A	A	A
Potassium Cyanide	A	A	A	A	A	A	A	A
Potassium Dichromate	A	A	A	B	A	A	A	A
Potassium Hydroxide (T<120F)	B	B	B	B	B	A	B	B
Potassium Nitrate	A	A	A	B	A	A	A	A
Potassium Permanganate	A	A	-	B	A	B	A	A
Potassium Sulfate	A	A	A	A	A	B	A	A
Producer Gás	A	A	B	C	A	B	A	C
Propane	A	A	B	C	A	B	A	B
Propyl Alcohol	A	A	A	A	A	A	A	A
Propyl Nitrate	C	C	C	C	C	C	C	C
Propylene	C	C	C	C	C	C	C	C
Propylene Oxide	C	C	C	C	C	C	C	C
Pyridine	C	C	C	C	C	C	C	C
Rapessed Oil	B	B	B	C	B	C	B	B
Refrigerants								
11	B	B	C	C	B	A	B	C
12	A	A	A	A	A	A	A	C
13	A	A	A	A	A	A	A	C
13 B1	A	A	A	A	A	A	A	C
21	C	C	C	C	C	C	C	C
22	C	C	A	A	C	A	C	C
31	C	C	B	B	C	B	C	C
32	A	A	A	A	A	A	A	C
112	B	B	C	C	B	B	B	C
113	A	A	A	B	A	A	A	C
114	A	A	A	A	A	A	A	C
114 B2	B	B	C	C	B	A	B	C
115	A	A	A	A	A	A	A	C
142b	A	A	A	A	A	A	A	C
152a	A	A	A	A	A	C	A	C
218	A	A	A	A	A	A	A	C
502	B	B	A	A	B	-	B	C
C316	A	A	A	A	A	A	A	C
C318	A	A	A	A	A	A	A	C
Salicylic Acid	B	B	A	B	B	-	B	B
Salt Water	A	A	B	A	A	A	A	A
Sea Water	A	A	A	A	A	A	A	A
Sewage	A	A	B	B	A	A	A	A
Silicone Oil	A	A	A	A	A	A	A	A
Silver Nitrate	A	B	A	B	B	A	B	B

\*Please see note at the end of this table.

R.072816

**Teadit North America.**

10545 Red Bluff Rd - Pasadena - TX - 77507

Phone: 281-476-3900 - Fax: 281-476-3999 - e-mail: sales@teadit.com - engineering@teadit.com - [www.teadit-na.com](http://www.teadit-na.com)



Sealing for a safer and greener tomorrow

# Chemical Compatibility Chart

## Compressed Fiber Gasket Materials

A: Suitable    B: Consult with TEADIT    C: Not recommended

FLUIDS	NA1001	NA1082SAN	NA1076	NA1080	NA1081	NA1085	NA1100	NA1122
Skydrol 500	C	C	C	C	C	C	C	C
Soap Solutions	A	A	B	A	A	A	A	A
Soda Ash	A	A	A	A	A	A	A	A
Sodium Bicarbonate	A	A	A	B	A	A	A	A
Sodium Bisulfate, Dry	A	A	-	B	A	A	A	A
Sodium Bisulfite	A	A	A	A	A	A	A	A
Sodium Carbonate	A	A	-	A	A	A	A	A
Sodium Chloride (T<120F)	A	A	A	A	A	A	A	A
Sodium Cyanide	A	A	A	A	A	A	A	A
Sodium Hydroxide (T≥120F)	C	C	C	C	C	C	C	C
Sodium Hydroxide (T<120F)	B	B	A	B	B	A	B	B
Sodium Hypochlorite	C	C	C	C	C	C	C	C
Sodium Metaphosphate	A	A	B	A	A	B	A	A
Sodium Nitrate	B	B	B	B	B	A	B	B
Sodium Perborate	B	B	B	B	B	B	B	B
Sodium Peroxide	B	B	B	B	B	B	B	B
Sodium Phosphate	A	A	B	A	A	A	A	A
Sodium Silicate	A	A	A	A	A	A	A	A
Sodium Sulfate	A	A	A	A	A	A	A	A
Sodium Sulfide	A	A	-	A	A	A	A	A
Sodium Thiosulfate	B	B	A	B	B	A	B	B
Soybean Oil	A	A	-	C	A	C	A	A
Stannic Chloride	A	A	B	A	A	-	A	A
Steam	A	A	B	A	A	B	A	A
Stearic Acid	A	A	B	A	A	B	A	A
Stoddard Solvent	A	A	B	C	A	C	A	-
Styrene	C	C	C	C	C	C	C	C
Styrene Oxide	C	C	-	C	C	C	C	C
Sulfur Chloride	C	C	C	C	C	C	C	C
Sulfur Dioxide	C	C	C	B	C	A	C	C
Sulfur, Molten	C	C	-	C	C	C	C	C
Sulfur Trioxide	C	C	C	C	C	C	C	C
Sulfuric Acid, oleum	C	C	C	C	C	C	C	C
Sulfuric Acid ≤ 90%	C	C	C	C	C	A	C	C
Sulfuric Acid 95%	C	C	C	C	C	B	C	C
Sulfuric Acid, Fuming	C	C	C	C	C	C	C	C
Sulfurous Acid	B	B	B	B	B	A	B	B
Tannic Acid	A	A	A	A	A	A	A	A
Tar (Asphalt)	B	B	C	C	B	C	B	B
Tartaric Acid	A	A	B	A	A	A	A	A
Tetrabromoethane	C	C	C	C	C	C	C	C

\*Please see note at the end of this table.

R.072816

**Teadit North America.**

10545 Red Bluff Rd - Pasadena - TX - 77507

Phone: 281-476-3900 - Fax: 281-476-3999 - e-mail: sales@teadit.com - engineering@teadit.com - [www.teadit-na.com](http://www.teadit-na.com)





Sealing for a safer and greener tomorrow

# Chemical Compatibility Chart

## Compressed Fiber Gasket Materials

A: Suitable    B: Consult with TEADIT    C: Not recommended

FLUIDS	NA1001	NA1082SAN	NA1076	NA1080	NA1081	NA1085	NA1100	NA1122
Tetrachloroethane	B	B	-	C	B	C	B	B
Tetrachloroethylene	C	C	C	C	C	C	C	C
Tetrahydrofuran, THF	C	C	C	C	C	C	C	C
Thionyl Chloride	C	C	C	C	C	C	C	C
Titanium Tetrachloride	B	B	C	C	B	C	B	B
Toluene	C	C	C	C	C	C	C	C
2,4-Toluenediisocyanate	C	C	C	C	C	C	C	C
Transformer Oil	A	A	B	C	A	B	A	B
Transmission Fluid A	A	A	B	C	A	C	A	A
Trichloroacetic Acid	B	B	C	C	B	C	B	B
1,1,2-Trichloroethane	C	C	C	C	C	C	C	C
Trichloroethylene	C	C	C	C	C	C	C	C
Trichlorotrifluoroethane	A	A	-	C	A	C	A	C
Tricresylphosphate	C	C	C	C	C	C	C	C
Triethanolamine -- TEA	B	B	A	B	B	A	B	B
Triethyl Aluminum	C	C	C	C	C	C	C	C
Triethylamine	C	C	-	-	C	-	C	C
Tung Oil	A	A	B	C	A	C	A	A
Turpentine	A	A	C	C	A	C	A	A
Varnish	C	C	C	C	C	C	C	C
Vegetable Oil	A	A	C	C	A	B	A	A
Vinegar	B	B	B	B	B	A	B	B
Vinyl Acetate	B	B	-	-	B	-	B	B
Vinyl Chloride	C	C	C	C	C	C	C	C
Vinylidene Chloride	C	C	-	C	C	C	C	C
Vinyl Methacrylate	C	C	-	C	C	C	C	C
Water, Oxidizing Salt	A	A	A	A	A	A	A	A
No Oxidizing Salt	A	A	A	A	A	A	A	A
Water, Distilled	A	A	A	A	A	A	A	A
Whiskey and Wines	A	A	A	A	A	A	A	A
Xylene	C	C	C	C	C	C	C	C
Zinc Chloride	A	A	A	A	A	A	A	A
Zinc Sulfate	A	A	A	B	A	A	A	A

**NOTE:** Properties and application parameters shown throughout this Compressed Fiber Gasket Materials Chemical Compatibility Chart are typical. Your specific application should not be undertaken without independent study and evaluation for suitability. For specific application recommendations consult with TEADIT. Failure to select proper sealing products could result in property damage and/or serious personal injury. Specifications subject to change without notice; this edition cancels all previous issues.

R.072816

**Teadit North America.**

10545 Red Bluff Rd - Pasadena - TX - 77507

Phone: 281-476-3900 - Fax: 281-476-3999 - e-mail: sales@teadit.com - engineering@teadit.com - [www.teadit-na.com](http://www.teadit-na.com)